

OMNILITH™ 500 EXTREME PRESSURE GREASE

Omnilith™ 500 is an extreme pressure grease suitable for use in severe applications across a wide variety of operating conditions including high load, moisture, and a wide speed range.

The lithium complex soap base allows for use at temperatures up to 450°F (232°C). Omnilith™ 500 EP 2 is the ideal choice as multipurpose grease in heavy-duty industry where extreme pressure or high temperature performance is required.

Maximum DN factor: 300,000 (NLGI Grade 2)
 Maximum continuous temperature: 350°F (177°C)
 Maximum occasional temperature: 450°F (232°C)
 Appearance: Red, Tacky

BENEFITS:

- RESISTS WEAR - extends equipment life.
- WATER RESISTANT - stays in place when exposed to moisture.
- CORROSION INHIBITED - protects metal parts from effects of oxidation.
- MECHANICALLY STABLE - resists separation. Excellent for pumping through automatic lubrication systems.

APPLICATIONS:

Universal grease for multiple applications, i.e. moisture, dust, vibration, shock loads, and extreme pressure. Use on electric motors, construction machines, vehicles, agricultural equipment, cranes, stackers, conveyor trolley bearings, and general industrial equipment. In wet or dirty environments, i.e. service stations, textile washing machines, pumps. In heavily loaded antifriction and plain bearings of mobile equipment, i.e. tie rod joints, universal joints, brake camshafts and splined shafts of motor vehicles, threaded spindles and guides of hoists, and bearing surfaces exposed to heavy loads.

ASTM #		TYPICAL CHARACTERISTICS	
	Grade	1.5	2
D-217	Cone Penetration (Worked)	290-320	265-295
D-566	Dropping Point, °F (°C)	500 (260)	500 (260)
D-445	Kinematic Viscosity (Base Oil without Polymer)		
	cSt @ 40°C	278	278
	cSt @ 100°C	22.5	22.5
D-445	Kinematic Viscosity (Base Oil with Polymer)		
	cSt @ 40°C	455	455
	cSt @ 100°C	31	31
Gardner Method	Density, lb/gl @ 60°F (15.5°C)	7.65	7.65
	Specific Gravity, g/cc @ 60°F (15.5°C)	0.920	0.919
D-2596	Four Ball EP, Weld Point, kg	800	800
D-2266	Four Ball Wear, Scar Width, mm	0.63	0.56
D-1264	Water Washout, % Loss	<5	<5
D-1743	Rust Test	Pass	Pass
D-4048 Modified	Copper Strip Corrosion for Greases 212°F (100°C) @ 3 hrs	Not Reported	1B
	Thickener Type	Lithium Complex	Lithium Complex
	Color	Red	Red
OEM Standard	Low Temperature Pumpability Lincoln Ventmeter @ 400 psi, °F (°C)	10 (-12)	10 (-12)
	Ambient temperature range, °F (°C)	0 (-18) to 300 (150)	0 (-18) to 300 (150)

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

Shuttle Tanks	Drums	Kegs	Pails	Cartridges 50 per case
---------------	-------	------	-------	---------------------------

For warranty information, scan the QR code.

whitmores.com

Made in the USA in an ISO 9001:2015 and ISO 14001:2015 Facility.

